

LGC MED / BTC

Yun, Su Hyun

Approved

LGC MED / BTC Ahn, Soon Ho

PRODUCT SPECIFICATION CONFIDENTIAL (TENTATIVE) Document No.

BCY-PS-MF1-Rev0

2011-08-19

Rev 0

Description

Lithium Ion ICR18650 MF1 2150mAh

PRODUCT SPECIFICATION (TENTATIVE)

Rechargeable Lithium Ion Battery Model: ICR18650 MF1 2150mAh



20 YOIDO-DONG YOUNGDUNGPO-GU, **SEOUL 150-721, KOREA**

TEL: (82) 2-3773-1114 FAX: (82) 2-3773-7005

http://www.lgchem.com



PRODUCT SPECIFICATION

CONFIDENTIAL (TENTATIVE)

<u>Document No.</u>

<u>Date</u>

BCY-PS-MF1-Rev0

Date 2011-08-19

<u>Rev</u>

Revision History

Revision	Date	Originator	Description
0	2011-08-19	Yun, Su Hyun	Original Release

LG Chem Lithium Ion ICR18650 MF1 2150mAh

PRODUCT SPECIFICATION

CONFIDENTIAL (TENTATIVE)

Document No. BCY-PS-MF1-Rev0 Date 2011-08-19

Rev 0

Contents

<u>Description</u>

Rev	/ision History2
Cor	ntents3
1. 0	General Information4
	1.1 Scope
	1.2 Application
	1.3 Product Classification
	1.4 Model Name
2. N	Iominal Specification
	2.1 Capacity
	2.2 Nominal Voltage
	2.3 Standard Charge
	2.4 Max. Charge Voltage
	2.5 Max. Charge Current
	2.6 Standard Discharge
	2.7 Max. Discharge Current
	2.8 Weight
	2.9 Operating Temperature
	2.10 Storage Temperature (for shipping state)
3. A	Appearance and Dimension5
	3.1 Appearance
	3.2 Dimension
4. F	Performance Specification5
	4.1 Standard Test Condition
	4.2 Electrical Specification
	4.3 Environmental Specification
	4.4 Mechanical Specification
	4.5 Safety Specification
5. C	Cautions and Prohibitions in Handling8

LG Chem Lithium Ion ICR18650 MF1 2150mAh

PRODUCT SPECIFICATION CONFIDENTIAL (TENTATIVE)

Document No. BCY-PS-MF1-Rev0

2011-08-19

Rev 0

1. General Information

1.1 Scope

Description

This product specification defines the requirements of the rechargeable lithium ion battery to be supplied to the Customer by LG Chem.

Light Electric Vehicle 1.2 Application:

1.3 Product classification: Cylindrical rechargeable lithium ion battery

ICR18650 MF1 1.4 Model name:

2. Nominal Specification

Item	Condition / Note	Specification
2.1 Capacity	Std. charge / discharge	Nominal 2,150 mAh (C _{nom})
2.1 Supacity	(Refer to 4.1.1./ 4.1.2)	Minimum 2,050 mAh (C _{min})
2.2 Nominal Voltage	Average for Std. discharge	3.65V
	Constant current	0.5C (1,075mA)
2.3 Standard Charge (Refer to 4.1.1)	Constant voltage	4.2V
,	End condition(Cut off)	50mA
2.4 Max. Charge Voltage		4.2V
2.5 Max. Charge Current		1.0C(2,150mA)
2.6 Standard Discharge	Constant current	0.2C (430mA)
(Refer to 4.1.2)	End voltage(Cut off)	2.75V
2.7 Max. Discharge Current		10A
2.8 Weight	Approx.	44.0 g
2.0 Operating Temperature	Charge	0 ~ 45℃
2.9 Operating Temperature	Discharge	-20 ~ 60℃
	1 month	-20 ~ 60 ℃
2.10 Storage Temperature (for shipping state ⁱ)	3 month	-20 ~ 45℃
	1 year	-20 ~ 20℃

^{*} Shipping state : About 40% capacity of fully charged state

Lithium Ion ICR18650 MF1 2150mAh

PRODUCT SPECIFICATION

CONFIDENTIAL (TENTATIVE)

Document No.
BCY-PS-MF1-Rev0

2011-08-19

<u>Rev</u>

3. Appearance and Dimension

3.1 Appearance


There shall be no such defects as deep scratch, crack, rust, discoloration or leakage, which may adversely affect the commercial value of the cell.

3.2 Dimension

Diameter : 18.3 + 0.1/-0.3 mm (Max. 18.4 mm)

Diameter is defined as the largest data value measured on the "A" area of a cylindrical cell.

Height : $65.0 \pm 0.2 \text{ mm}$ (Max. 65.2 mm)



4. Performance Specification

4.1 Standard test condition

4.1.1 Standard Charge

Unless otherwise specified, "Standard Charge" shall consist of charging at constant current of 1,075mA. The cell shall then be charged at constant voltage of 4.2V while tapering the charge current. Charging shall be terminated when the charging current has tapered to 50mA. For test purposes, charging shall be performed at 25° C \pm 2° C.

4.1.2 Standard Discharge

"Standard Discharge" shall consist of discharging at a constant current of 430mA to 2.75V. Discharging is to be performed at 25 $^{\circ}$ C \pm 2 $^{\circ}$ C unless otherwise noted (such as capacity versus temperature).

4.1.3 Fast Charge / discharge condition

Cells shall be charged at constant current of 2,150mA to 4.2V with end current of 107.5mA. Cells shall be discharged at constant current of 2,150mA to 2.75V. Cells are to rest 30 minutes after charge and 30 minutes after discharge.

LG Chem Lithium Ion ICR18650 MF1 2150mAh

PRODUCT SPECIFICATION

CONFIDENTIAL (TENTATIVE)

Document No. BCY-PS-MF1-Rev0

2011-08-19

Rev 0

4.2 Electrical Specification

Description

Item	Condition	Specification
4.2.1	Cell shall be measured at 1kHz after charge per	\leq 35 m Ω , without PTC
Initial AC Impedance	4.1.1.	
4.2.2	Cells shall be charged per 4.1.1 and discharged	$C_{ini} \geq 2,050 \text{ mAh } (C_{min})$
Initial Capacity	per 4.1.2 within 1h after full charge.	
4.2.3	Cells shall be charged and discharged per	\geq 70 % (of C _{min} in 2.1)
Cycle Life	4.1.3, 500 cycles. A cycle is defined as one	
	charge and one discharge. 501st discharge	
	capacity shall be measured per 4.1.1 and 4.1.2	

4.3 Environmental specification.

Item	Condition	Specification
4.3.1	Cells shall be charged per 4.1.1 and stored in a	Capacity remaining rate
Storage Characteristics	temperature-controlled environment at 25°C ±	≥ 90% (C _{ini} in 2.1)
	2°C for 30 days. After storage, cells shall be	
	discharged per 4.1.2 to obtain the remaining	
	capacity.*	
4.3.2	Cells shall be charged per 4.1.1 and stored in a	No leakage,
High Temperature	temperature-controlled environment at 60°C for	Capacity recovery rate ≥
Storage Test	1 week. After storage, cells shall be discharged	80%
	per 4.1.2 and cycled per 4.1.3 for 3 cycles to	
	obtain recovered capacity*.	
4.3.3	Cells are charged per 4.1.1 and stored at 60°C	No leakage, No rust
High Temperature and	(95% RH) for 168 hours. After test, cells are	Capacity recovery rate ≥
High Humidity Test	discharged per 4.1.2 and cycled per 4.1.3 for 3	80%
	cycles to obtain recovered capacity.	
4.3.4	65°C (8h) \leftarrow 3hrs \rightarrow -20°C (8h) for 8 cycles	No leakage
Thermal Shock Test	with cells charged per 4.1.1 After test, cells are	Capacity recovery rate ≥
	discharged per 4.1.2 and cycled per 4.1.3 for 3	80%
	cycles to obtain recovered capacity.	

^{*} Remaining Capacity: After storage, cells shall be discharged with Std. condition(4.1.2) to measure the remaining capacity.

** Recovery Capacity: After storage, cells shall be discharged with fast discharge condition(4.1.3), and then cells shall be charged with std. charge condition(4.1.1), and then discharged with Std. condition(4.1.2). This charge / discharge cycle shall be repeated three times to measure the recovery capacity.

PRODUCT SPECIFICATION CONFIDENTIAL (TENTATIVE)

LG Chem

<u>Description</u>
Lithium Ion ICR18650 MF1 2150mAh

Document No. BCY-PS-MF1-Rev0 Date 2011-08-19

<u>Rev</u>

4.3.5	Cells shall be charged	Cells shall be charged per 4.1.1 at 23°C ± 2°C	
Temperature	and discharged per	4.1.2 at the following	
Dependency of	temperatures.		
Capacity	Charge	Discharge	Capacity
		-10℃	70% of C _{ini}
	22 %	0℃	80% of C _{ini}
	23℃	23℃	100% of C _{ini}
		60℃	95% of C _{ini}

4.4 Mechanical Specification

Item	Condition	Specification
4.4.1	Cells charged per 4.1.1 are dropped onto an oak board	No leakage
Drop Test	from 1 meter height for 1 cycle, 2 drops from each cell	No temperature rising
	terminal and 1 drop from side of cell. (Total number of	
	drops =3).	
4.4.2	Cells charged per 4.1.1 are vibrated for 90 minutes per	No leakage
Vibration Test	each of the three mutually perpendicular axes (x, y, z)	
	with total excursion of 0.8mm, frequency of 10Hz to	
	55Hz and sweep of 1Hz change per minute.	

4.5 Safety Specification

Item	Condition	Specification
	Cells are discharged per 4.1.2, then charged at constant	
4.5.1	current of 3 times the max. charge condition and	No evalede No fire
Overcharge Test	constant voltage of 4.2V while tapering the charge	No explode, No fire
	current. Charging is continued for 7 hours (Per UL1642).	
4.5.2	Cells are charged per 4.1.1, and the positive and	
External Short -	negative terminal is connected by a $100m\Omega$ -wire for 1	No explode, No fire
Circuiting Test	hour (Per UL1642).	
4,5.3	Calle are discharged at constant current of 0.20 to	
Overdischarge	Cells are discharged at constant current of 0.2C to	No explode, No fire
Test	250% of the minimum capacity.	

.G Chem

Description

PRODUCT SPECIFICATION CONFIDENTIAL (TENTATIVE)

Document No.

2011-08-19

<u>Date</u>

Rev 0

Lithium Ion ICR18650 MF1 2150mAh BCY-PS-MF1-Rev0

4.5.4 Heating Test	Cells are charged per 4.1.1 and heated in a circulating air oven at a rate of 5°C per minute to 130°C. At 130°C, oven is to remain for 10 minutes before test is discontinued (Per UL1642).	No explode, No fire
4.5.5 Impact Test	Cells charged per 4.1.1 are impacted with their longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8mm diameter bar (Per UL1642).	No explode, No fire
4.5.7 Crush Test	Cells charged per 4.1.1 are crushed with their longitudinal axis parallel to the flat surface of the crushing apparatus (Per UL1642).	No explode, No fire

5. Caution and Prohibition in Handling

Warning for using the lithium ion rechargeable battery. Mishandling of the battery may cause heat, fire and deterioration in performance. Be sure to observe the following.

Caution

- When using the application equipped with the battery, refer to the user's manual before usage.
- Please read the specific charger manual before charging.
- Charge time should not be longer than specified in the manual.
- When the cell is not charged after long exposure to the charger, discontinue charging.
- Battery must be charged at operating temperature range 0 ~ 45 °C.
- Battery must be discharged at operating temperature range -20 ~ 60 °C.
- Please check the positive(+) and negative(-) direction before packing.
- When a lead plate or wire is connected to the cell for packing, check out insulation not to short-circuit.
- Battery must be stored separately.
- Battery must be stored in a dry area with low temperature for long-term storage.
- Do not place the battery in direct sunlight or heat.
- Do not use the battery in high static energy environment where the protection device can be damaged.
- When rust or smell is detected on first use, please return the product to the seller immediately.
- The battery must be away from children or pets
- When cell life span shortens after long usage, please exchange to new cells.



PRODUCT SPECIFICATION

CONFIDENTIAL (TENTATIVE)

BCY-PS-MF1-Rev0

2011-08-19

<u>Date</u>

<u>Rev</u>

Prohibitions

- Do not use different charger. Do not use cigarette jacks (in cars) for charging.
- Do not charge with constant current more than maximum charge current.
- Do not disassemble or reconstruct the battery.
- Do not throw or cause impact.
- Do not pierce a hole in the battery with sharp things. (such as nail, knife, pencil, drill)
- Do not use with other batteries or cells.
- Do not solder on battery directly.
- Do not press the battery with overload in manufacturing process, especially ultrasonic welding.
- Do not use old and new cells together for packing.
- Do not expose the battery to high heat. (such as fire)
- Do not put the battery into a microwave or high pressure container.
- Do not use the battery reversed.
- Do not connect positive(+) and negative(-) with conductive materials (such as metal, wire)
- Do not allow the battery to be immerged in or wetted with water or sea-water.